

Lines in the Feature

These three lines were created, one exactly alongside the defect edge. The dimensions for the lines starting from left are:

1.H 15 nm W 162 nm T 6 min

2.H 10 nm W 150 nm T 5 min

3.H 5 nm W 138 nm T 4 min





Figure 19

Sol-Gel in Features by FIBICS



An attempt to fill up a hole in features made with FIB. The average height of the feature deposited is 46 nm. A SiN_3 tip was used in this experiment.

Sol-Gel composition same as mentioned before. Dwelling time was 14 min. The deposited structure were cured at 120°C for 6 min.

Figure 21